

EXPRESS™ TruTouch™ NITRILE EXAMINATION GLOVES, POWDER FREE, NON-STERILE

Design and Feature	Ambidextrous, textures surface at fingers (E1) and beaded cuff	
Type	Powder free and non-sterile examination gloves	
Material	100% nitrile (Acrylonitrile-butadiene)	
Color	Blue	
Surface Treatment	Chlorination on donning side	
Powder Free Residue (mg/glove)	≤ 2	
Dimension	Palm width (mm)	Length (mm)
XS	≤80	Min. 240
S	80±10	Min. 240
M	95±10	Min. 240
L	110±10	Min. 240
XL	≥110	Min. 240
Weight (g)		
XS	2.3±0.3	
S	2.5±0.3	
M	2.7±0.3	
L	3.0±0.3	
XL	3.3±0.3	
Single-wall Thickness (mm) * All Sizes	Finger	0.08±0.02
	Palm	Min. 0.05
	Cuff	Min. 0.05
Physical Properties	Before Aging	EN/ASTM Spec
	Tensile Strength (MPa)	Min 14
	Elongation (%)	Min 500
	Force at Break (N)	Min 6
Physical Properties	After Aging	EN/ASTM Spec
	Tensile Strength (MPa)	Min 14
	Elongation (%)	Min 400
	Force at Break (N)	Min 6
Packing Mode	100 gloves by weight per dispenser and 10 per carton	
Packing Measurement	Box Dimension	23.00 cm x 11.00 cm x 6.50 cm
	Carton Dimension	34.00 cm x 23.50 cm x 24.00 cm
	Weight per box	S Size 260g, M Size 280g, L Size 310g, XL Size 340g
	Weight per carton	S Size 2700g, M Size 2900g, L Size 3200g, XL Size 3500g
Glove Marking	No Marking	
Lot # identification on Finished Goods	Lot Number Structure: LOT YYYYMMBB (8 digits)	
	YYYY = Year of Packing	
	MM = Month of Packing	
	BB = Batch Number	
Recommended Shelf Life	5 years upon manufactured date.	
Pre-shipment inspection *Single- Normal Sampling Plan	Dimension	N=13, Median
	Physical Properties	N=13, Median
	100ml Water Leak	G-I, AQL 1.5 – AQL 4.0
	Powder Free Residue	N=5
	Major Visual Inspection	G-I, AQL 2.5
	Minor Visual Inspection	G-I, AQL 4.0
Quality Assurance	FDA, FDA 510k	
	CE Medical Device Directive 93/42/EEC Class I	
	EN 455-1:2000, EN 455-2:2015, EN 455-3:2015	
	ASTM D6319, ASTM D6124 and ASTM D5712	

Note: The Above information is a guideline of typical performance value and characteristics of the product; and not to be used as actual product specifications.